



111.17

H&C®

CONCRETE SEALER
WET LOOK WATER BASED

PRODUCT DESCRIPTION

H&C® Wet Look Sealer is a premium quality 100% clear acrylic sealer that will enhance and protect previously coated, bare concrete and other masonry surfaces. This single component, solvent free, VOC compliant sealer can be applied for both interior and exterior applications. H&C® Wet Look Sealer will apply milky white to ensure complete coverage, but dries to a clear transparent finish.

Where to use:

- Topcoat for stained or painted surfaces
- Patios
- Lanais
- Driveways
- Walkways
- Pool Decks
- Brick and stucco surfaces

Acceptable Standards:

Meets MPI (Master Painters Institute) #99 Sealer, Water Based for Concrete Floors

CHARACTERISTICS

Color: Applies Milky White Dries Clear

Coverage	sq ft/gal
Previously coated concrete	200-300
Porous Concrete	100-200
Concrete Block	100-150
Porous Decorative Block	75-100
Brick (clay)	100-150

Drying Time, @77°F, 50% RH:

temperature and humidity dependent	
To Touch:	1 hour
Recoat:	2 hours
Light traffic:	24 hours
Heavy traffic:	72 hours

*NOTE: High humidity and /or low temperatures will affect drying time.

Finish:	Gloss
Vehicle Type:	Acrylic
VOC (less exempt solvents):	98 g/L
Volume Solids:	27% +/-1%

Coefficient of Friction

Without H&C® SharkGrip:	.7
With H&C® SharkGrip:	.85

Taber Abrasion:

Good after 1 week cure time

Chemical Resistance:	Good
-----------------------------	------

SURFACE PREPARATION

WARNING! Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup. For more information, call the National Lead Information Center at 1-800-424-LEAD (in US) or contact your local health authority.

Bare Concrete:

Freshly placed concrete must be a minimum of 28 days old. All concrete should be clean and free of laitance, oil, grease and mildew. If mold, mildew or fungus is present, kill and remove with a solution of one-cup household bleach to one gallon of water. Wear protective eyewear, waterproof gloves, and protective clothing. Quickly wash off any of the mixture that comes into contact with your skin. **DO NOT ADD DETERGENTS OR AMMONIA TO THE BLEACH/WATER SOLUTION.** Concrete MUST be etched, with H&C® Concrete Etcher or muriatic acid, following label directions. The surface should have the feel of 120-grit sandpaper, if not then a second etching is required. Allow 24 hours before staining. Cured concrete should have a pH level between 6 and 10.



H&C[®] CONCRETE SEALER WET LOOK WATER BASED

SURFACE PREPARATION

Previously Stained or Painted:

Make sure all previously painted or stained surfaces are in sound condition. Scrape and sand all loose material prior to the application of the H&C[®] Wet Look Sealer. To ensure adequate adhesion of sealer, scuff sand all remaining stain or paint. Reapplication of the old coating should be done to create an even uniform appearance. H&C[®] Cleaner Degreaser mixed to a 50/50 ratio with water will remove light soil from the surface. H&C[®] Cleaner Degreaser should be used full strength on heavy oil and grease stains. Refer to the H&C[®] Cleaner Degreaser label for specific instructions.

APPLICATION

Determine if conditions are proper for application:

For best results, surface and air temperature should be above 50°F and below 95°F. Temperature should not fall below 40°F for 24 hours following application. Do not apply H&C[®] Wet Look Sealer if rain is imminent or expected within 12 hours of application.

Slip Resistance

Some surfaces may require a slip-resistant additive for safety. Add **H&C[®] SharkGrip Slip Resistant Additive** to the final coat, following label directions. **H&C[®] SharkGrip Slip Resistant Additive** should not be used in place of a non-skid finish.

APPLICATION

This product can be applied with a brush and roller or airless spray equipment. Brushes and Rollers should be of synthetic material and nap thickness should not exceed 3/8". If airless spraying, tip orifice should not exceed .017". When spraying, back roll sealer to remove excess sealer, which will ensure an even finish. Freshly stained or painted surfaces will require cure time before any application of H&C[®] Wet Look Sealer. Refer to the individual product instructions for minimum recoat time. One coat of H&C[®] Wet Look Sealer is normally sufficient for previously painted or stained surfaces. Two coats sealer may be required for bare concrete to improve final appearance. If a second coat is desired allow a minimum of 2 hours dry time between coats. Do not over apply as "blushing" may result. Contact H&C[®] Technical Services if blushing persists (800-867-8246). Approximate coverage will be 200-300 square feet per gallon on previously painted or stained surfaces. The coverage will vary depending on the texture and density of the concrete. The H&C[®] Wet Look Sealer will apply milky white and dry clear in approximately 1 hour. Vertical surfaces, such as concrete, block or brick walls, should be coated in the same manner as described above.

CLEANUP INFORMATION

Clean sprayer and tools with soap and water immediately after use. Spray clear water through the line of the sprayer until the water runs clear.

MAINTENANCE

Clean light to medium soiled surfaces with a 50/50 solution of H&C[®] Cleaner Degreaser to water. Use H&C[®] Cleaner Degreaser at full strength for heavy soiled areas, such as oil and grease stains. If H&C[®] Cleaner Degreaser is not available, use a good quality neutral based cleaner degreaser following manufacturer's directions for use.

TECHNICAL SERVICES

1-800-TO STAIN(867-8246)
www.hc-concrete.com

ORDERING INFORMATION

Part Numbers

Gallon 50.048054-16

Five 50.048055-20

SMIS Numbers

Gallon 155-6497

Five 155-6505

WARNING

- Use with adequate ventilation
- Keep out of the reach of children
- Use a NOISH approved respirator, when necessary
- Do not take internally
- In case of ingestion, CALL A PHYSICIAN immediately. DO NOT induce vomiting

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of H&C concrete coatings and The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your H&C or Sherwin-Williams representative to obtain the most recent Product Data sheet